

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
18 September 2003 (18.09.2003)

PCT

(10) International Publication Number
WO 03/076510 A1

- (51) International Patent Classification⁷: **C08L 23/12**,
23/16, 23/10, 23/04, C08J 5/18 **Katsuharu [JP/JP]**; 109-1, Hakuraku, Kanagawa-ku,
Yokohama-city (JP).
- (21) International Application Number: PCT/EP03/02633 (74) Agents: **GAVERINI, Gaetano**; Basell Poliolefine Italia
S.p.A., Intellectual Property, Via Pergolesi, 25, I-20124 Mi-
lano et al. (IT).
- (22) International Filing Date: 10 March 2003 (10.03.2003)
- (25) Filing Language: English (81) Designated States (*national*): JP, US.
- (26) Publication Language: English (84) Designated States (*regional*): European patent (AT, BE,
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU,
IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).
- (30) Priority Data:
2002-069957 14 March 2002 (14.03.2002) JP
- (71) Applicant (*for all designated States except US*): **BASELL
POLIOLEFINE ITALIA S.P.A.** [IT/IT]; Via Pergolesi,
25, I-10124 Milano (IT).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **FUDABA, Tetsuya**
[JP/JP]; 624-1, Berude Ohmiya B403, Higashioonari-
cho 1-chome, Saitama-city (JP). **MITARAI, Nobuyuki**
[JP/JP]; Showadenko Ichigao-ryo, 12-33, Edanishi
1-chome, Aoba-ku, Yokohama-city (JP). **TAGASHIRA,**
- Declarations under Rule 4.17:**
— *as to the applicant's entitlement to claim the priority of the
earlier application (Rule 4.17(iii)) for all designations*
— *of inventorship (Rule 4.17(iv)) for US only*
- Published:**
— *with international search report*
- For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: POLYPROPYLENE RESIN COMPOSITION AND FILM THEREOF

(57) **Abstract:** A polypropylene resin composition comprising (by weight) 40 to 80% of a polypropylene component (A) comprising a copolymer of propylene with ethylene and/or a C₄₋₁₂ α-olefin, or a homopolymer of propylene, and 20 to 60% of a copolymer component (B) containing a copolymer (B-1) and a copolymer (B-2), wherein both (B-1) and (B-2) are copolymers of propylene with ethylene and/or a C₄₋₁₂ α-olefin, in (B-1) the amount of units derived from propylene is from more than 50% by weight to 85% by weight, and in (B-2) the amount of units derived from propylene is 15 to 50% by weight, the molecular weight distribution (Mw/Mn) is 3.0 or less, and blockness (CSD) determined using the measured NMR values is 1.3 or less; in which composition the amount of (B-2) with respect to the whole polypropylene resin composition is 3% or more, and the ratio of the limiting viscosity of (B-1) to the viscosity of (A) ([η]B-1/[η]A) is 1.5 or less, and the ratio of the limiting viscosity of (B-1) to the viscosity of (B-2)